

# SAFETY DATA SHEET (1907/2006)

#### R0718410

Revision Date: 2017-07-12 Version: 2

#### 2-Butyne-1,4-diol pastilles

# ANNEX

1. Overvie	w of exposure scenarios	4
2. Exposu	re Scenario 1: Manufacture and processinG of 1,4-butynediol as an isolated intermediate under strictly control	led
conditions		5
2.1. De	scription of Exposure Scenario	5
2.2. En	vironment contributing scenario	5
2.2.1.	Manufacture of the substance (ERC 1)	5
2.2.1	1. Conditions of use	5
2.2.1	2. Local releases to the environment	6
2.3. Wo	orker contributing scenario	6
2.3.1.	Chemical production or refinery in closed process without likelihood of exposure or processes with	
equivale	ent containment conditions (PROC 1)	6
2.3.1	1. Conditions of use	6
2.3.2.	Chemical production or refinery in closed continuous process with occasional controlled exposure or	
process	es with equivalent containment conditions (PROC 2)	7
2.3.2	1. Conditions of use	7
2.3.3.	Manufacture or formulation in the chemical industry in closed batch processes with occasional controlled	d
exposur	e or processes with equivalent containment condition (PROC 3)	7
2.3.3	1. Conditions of use	7
3. EXPOS	URE SCENARIO 2: Manufacture - Manufacture and bulk handling of 1,4-Butynediol (flake) in continuous or	r
batch process	5es	9
3.1. De	scription of Exposure scenario	9
3.2. En	vironment contributing scenario	9
3.2.1.	Manufacture of the substance (ERC 1)	9
3.2.1	1. Conditions of use	9
3.2.1	2. Local releases to the environment	10
3.3. Wo	orker contributing scenario	10
3.3.1.	Mixing or blending in batch processes (PROC 5)	10
3.3.1	1. Conditions of use	10
3.3.2.	Transfer of substance or mixture (charging and discharging) at non-dedicated facilities (PROC 8a)	11
3.3.2	1. Conditions of use	11
3.3.3.	Transfer of substance or mixture (charging and discharging) at dedicated facilities (PROC 8b)	11
3.3.3	1. Conditions of use	11
3.3.4.	Transfer of substance or mixture into small containers (dedicated filling line, including weighing) (PRO	C 9)
	12	
3.3.4	1. Conditions of use	12
3.3.5.	Tabletting, compression, extrusion, pelletisation, granulation (PROC 14)	13
3.3.5	1. Conditions of use	13
4. EXPOS	URE SCENARIO 3: Formulation or re-packing - Manufacture and bulk handling of 1,4-Butynediol (flake) in	
continuous o	r batch processes	14
4.1 De	scription of Exposure scenario	14

	nment contributing scenario	14
4.2.1.	Formulation into mixture (ERC 2)	14
4211	Conditions of use	14
4212	Local releases to the environment	15
4.2 Worker	contributing scanario	15
4.3. WOIKCI	Mixing or blanding in batch processes 100% (DBOC 5)	15
4.3.1.	Conditions of open and the processes - 100% (PROC 5)	15
4.3.1.1.		15
4.3.2.	Mixing or blending in batch processes - 5% (PROC 5)	10
4.3.2.1.	Conditions of use	16
4.3.3.	Mixing or blending in batch processes - 1% up to 60 °C (PROC 5)	16
4.3.3.1.	Conditions of use	16
4.3.4.	Transfer of substance or mixture (charging and discharging) at non-dedicated facilities – 100% (PROC 8a)	17
4.3.4.1.	Conditions of use	17
4.3.5.	Transfer of substance or mixture (charging and discharging) at non-dedicated facilities - 5% (PROC 8a)	18
4.3.5.1.	Conditions of use	18
4.3.6.	Transfer of substance or mixture (charging and discharging) at dedicated facilities - 100% (PROC 8b)	18
4.3.6.1.	Conditions of use	18
4.3.7.	Transfer of substance or mixture (charging and discharging) at dedicated facilities - 5% (PROC 8b)	19
4.3.7.1.	Conditions of use	19
4.3.8.	Transfer of substance or mixture into small containers (dedicated filling line, including weighing) – 100%	
(PROC 9)	20	
4381	Conditions of use	20
139	Transfer of substance or mixture into small containers (dedicated filling line including weighing) $-25\%$	20
$(\mathbf{PPOC} 0)$	25.0	
(1  KOC  3)	20 Conditions of use	20
4.5.9.1.	Conditions of use	20
4.3.10.	Transfer of substance or mixture into small containers (dedicated filling line, including weigning) – 5% up $(20)$	10 21
40 °C (PRO	C 9)	21
4.3.10.1.	Conditions of use	21
4.3.11.	Transfer of substance or mixture into small containers (dedicated filling line, including weighing) – 5% up	to
60 °C (PRO	С 9)	.22
4.3.11.1.	Conditions of use	22
4.3.12.	Tabletting, compression, extrusion, pelletisation, granulation (PROC 14)	22
4.3.12.1.	Conditions of use	22
5. EXPOSURE	E SCENARIO 4: Use at industrial sites - Use and handling of coatings, electroplating, cleaning / brightening	
and surface appli		5,
· · · · · · · · · · · · · · · · · · ·	cation of anti-corrosion solutions containing 1,4-Butynediol	g, 24
5.1. Descrip	cation of anti-corrosion solutions containing 1,4-Butynediol	g, 24 24
5.1. Descrip 5.2. Enviro	cation of anti-corrosion solutions containing 1,4-Butynediol btion of Exposure scenario	g, 24 24 24
5.1. Descrip 5.2. Environ 5.2.1.	cation of anti-corrosion solutions containing 1,4-Butynediol otion of Exposure scenario nment contributing scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4)	g, 24 24 24 24
5.1. Descrip 5.2. Environ 5.2.1.	cation of anti-corrosion solutions containing 1,4-Butynediol otion of Exposure scenario ment contributing scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4) Conditions of use	g, 24 24 24 24 24 24
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2	cation of anti-corrosion solutions containing 1,4-Butynediol btion of Exposure scenario ument contributing scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4) Conditions of use	g, 24 24 24 24 24 24
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Workey	cation of anti-corrosion solutions containing 1,4-Butynediol btion of Exposure scenario ument contributing scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4) Conditions of use Local releases to the environment	g, 24 24 24 24 24 24 25 25
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken	cation of anti-corrosion solutions containing 1,4-Butynediol bution of Exposure scenario	24 24 24 24 24 24 25 25
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worker 5.3.1. 5.3.1.1	cation of anti-corrosion solutions containing 1,4-Butynediol bution of Exposure scenario ument contributing scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4) Conditions of use Local releases to the environment contributing scenario Industrial spraying - 5% (PROC 7)	g, 24 24 24 24 24 25 25 25
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worker 5.3.1. 5.3.1.1.	cation of anti-corrosion solutions containing 1,4-Butynediol bution of Exposure scenario	g, 24 24 24 24 24 25 25 25 25 25
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.1.1. 5.3.2.	cation of anti-corrosion solutions containing 1,4-Butynediol bition of Exposure scenario ument contributing scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4) Conditions of use Local releases to the environment contributing scenario Industrial spraying - 5% (PROC 7) Conditions of use Industrial spraying - 1% (PROC 7) Conditions of use	<ul> <li>g,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>26</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li>g,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>26</li> <li>27</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.1.1. 5.3.2. 5.3.2.1. 5.3.2.1. 5.3.2.1.	cation of anti-corrosion solutions containing 1,4-Butynediol bution of Exposure scenario	<ul> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>26</li> <li>27</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2.1. 5.3.3.1. 5.3.3.1.	cation of anti-corrosion solutions containing 1,4-Butynediol bution of Exposure scenario	<ul> <li>g.</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>26</li> <li>27</li> <li>27</li> <li>27</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.3.1. 5.3.4.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li>g,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>27</li> <li>27</li> <li>27</li> <li>27</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li>g,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>27</li> &lt;</ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2. 5.3.3.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1. 5.3.5.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li>g,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>27</li> <li>27</li> <li>27</li> <li>27</li> <li>27</li> <li>28</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2. 5.3.3.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1. 5.3.5. 5.3.5.1.	cation of anti-corrosion solutions containing 1,4-Butynediol	g, 24 24 24 24 25 25 25 25 25 25 26 27 27 27 27 27 28 28
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2. 5.3.3.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4. 5.3.5. 5.3.5.1. 5.3.6.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li>g,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>27</li> <li>27</li> <li>28</li> <li>29</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1. 5.3.5. 5.3.5.1. 5.3.6. 5.3.6.1.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li><sup>5</sup>,</li> <li><sup>24</sup></li> <li><sup>24</sup></li> <li><sup>24</sup></li> <li><sup>24</sup></li> <li><sup>24</sup></li> <li><sup>25</sup></li> <li><sup>25</sup></li> <li><sup>25</sup></li> <li><sup>25</sup></li> <li><sup>26</sup></li> <li><sup>27</sup></li> <li><sup>27</sup></li> <li><sup>27</sup></li> <li><sup>28</sup></li> <li><sup>29</sup></li> <li><sup>29</sup></li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1. 5.3.5. 5.3.5.1. 5.3.6. 5.3.6.1. 5.3.7.	cation of anti-corrosion solutions containing 1,4-Butynediol	<ul> <li>5,</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>24</li> <li>25</li> <li>25</li> <li>25</li> <li>26</li> <li>27</li> <li>27</li> <li>28</li> <li>29</li> <li>29</li> <li>29</li> </ul>
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worken 5.3.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1. 5.3.5. 5.3.5.1. 5.3.6. 5.3.6.1. 5.3.7. 5.3.7.1.	cation of anti-corrosion solutions containing 1,4-Butynediol	5, 24 24 24 25 25 25 25 26 27 27 27 27 28 29 29 29 29
5.1. Descrip 5.2. Envirol 5.2.1. 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worker 5.3.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.4.1. 5.3.5. 5.3.5.1. 5.3.6. 5.3.6.1. 5.3.7. 5.3.7.1. 5.3.8.	cation of anti-corrosion solutions containing 1,4-Butynediol	5, 24 24 24 25 25 25 25 26 27 27 27 27 28 29 29 29 30
5.1. Descrip 5.2. Envirol 5.2.1. 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worker 5.3.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.5.1. 5.3.6. 5.3.6.1. 5.3.7. 5.3.8.1	cation of anti-corrosion solutions containing 1,4-Butynediol	5, 24 24 24 25 25 25 25 26 27 27 27 28 29 29 29 20 30 30
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worker 5.3.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.5. 5.3.5.1. 5.3.6. 5.3.6.1. 5.3.7. 5.3.8. 5.3.8.1. 5.3.9	cation of anti-corrosion solutions containing 1,4-Butynediol tion of Exposure scenario Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4) Conditions of use Local releases to the environment contributing scenario Industrial spraying - 5% (PROC 7) Conditions of use Industrial spraying - 1% (PROC 7) Conditions of use Transfer of substance or mixture (charging and discharging) at nondedicated facilities - 25% (PROC 8a) Conditions of use Transfer of substance or mixture (charging and discharging) at non-dedicated facilities - 5% (PROC 8a) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 100% (PROC 8b) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 25% (PROC 8b) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 5% (PROC 8b) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 25% (PROC 8b) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 25% (PROC 8b) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 5% (PROC 8b) Conditions of use Transfer of substance or mixture (charging and discharging) at dedicated facilities - 5% (PROC 8b) Conditions of use Roller application and brushing - 25% (PROC 10) Conditions of use Roller application or brushing - 5% (PROC 10)	5, 24 24 24 25 25 25 25 25 25 25 25 25 25 25 25 25
5.1. Descrip 5.2. Environ 5.2.1. 5.2.1. 5.2.1.1. 5.2.1.2. 5.3. Worker 5.3.1. 5.3.2. 5.3.2.1. 5.3.2. 5.3.2.1. 5.3.3. 5.3.3.1. 5.3.4. 5.3.5. 5.3.5.1. 5.3.6. 5.3.6.1. 5.3.7. 5.3.8. 5.3.8.1. 5.3.9. 5.3.9.	cation of anti-corrosion solutions containing 1,4-Butynediol	5, 24 24 24 25 25 25 25 25 25 25 25 25 25 25 25 25

5.3.10.	Treatment of articles by dipping and pouring - 25% (PROC 13)	31	
5.3.10.1.	Conditions of use	31	
5.3.11.	Treatment of articles by dipping and pouring - 5% (PROC 13)		
5.3.11.1.	1. Conditions of use		
6. EXPOSURE	RE SCENARIO 5: Use at industrial sites - Use of 1,4-Butynediol in laboratories		
6.1. Descrip	ption of Exposure scenario	33	
6.2. Enviror	ment contributing scenario	33	
6.2.1.	Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4)	33	
6.2.1.1.	Conditions of use	33	
6.2.1.2.	Local releases to the environment	33	
6.3. Worker	contributing scenario	34	
6.3.1.	Use as laboratory reagent (PROC 15)	34	
6.3.1.1.	Conditions of use	34	
7. EXPOSURE	SCENARIO 6: Widespread use by professional workers - Use and handling of coatings, electroplating,	25	
cleaning / brighte	ning, and surface application of anti-corrosion solutions containing 1,4-Butynediol		
7.1. Descrip	otion of Exposure scenario	35	
7.2. Enviroi	iment contributing scenario		
7.2.1.	Widespread use of non-reactive processing aid (no inclusion into or onto article, indoor) (ERC 8a)	35	
7.2.1.1.	Conditions of use		
7.2.1.2.	Local releases to the environment.		
7.2.2.	Widespread use of reactive processing aid (no inclusion into or onto article, indoor) (ERC 8b)		
7.2.2.1.	Conditions of use		
7.2.2.2.	Local releases to the environment.	30	
7.2.3.	widespread use of non-reactive processing and (no inclusion into or onto article, outdoor) (EKC 8d)		
7.2.3.1.	Local releases to the environment		
7.2.3.2.	Local releases to the environment		
7.2.4.	Conditions of use		
7.2.4.1.	L cool releases to the environment		
7.2.4.2. 7.3 Workov	contributing scenario		
7.3. WOIKE	Poller application or bruching 5% (PPOC 10)		
7.3.1.	Conditions of use		
7.3.1.1.	Roller application or bruching 1% (PROC 10)		
7321	Conditions of use	38	
733	Non industrial spraying - 1% (PROC 11)	38	
7331	Conditions of use	38	
734	Treatment of articles by dipping and pouring - 25% (PROC 13)	39	
7341	Conditions of use	39	
735	Treatment of articles by dipping and pouring - 5% (PROC 13)	40	
7351	Conditions of use	40	
8 EXPOSURE	E SCENARIO 7: Widespread use by professional workers - Use of 1 4-Butynediol in laboratories	41	
8.1. Descrit	ption of Exposure scenario.	41	
8.2. Enviro	ment contributing scenario.	41	
8.2.1.	Widespread use of non-reactive processing aid (no inclusion into or onto article, indoor) (ERC 8a)	41	
8.2.1.1.	Conditions of use	41	
8.2.1.2	Local releases to the environment.	41	
8.3. Worker	contributing scenario	41	
8.3.1.	Use as laboratory reagent - 100% (PROC 15)	41	
8.3.1.1.	Conditions of use	41	
8.3.2.	Use as laboratory reagent - 25% formulation (PROC 15).	42	
8.3.2.1.	Conditions of use	42	

# 1. OVERVIEW OF EXPOSURE SCENARIOS

ES#	Exposure scenario (ES) name
ES1 (M)	Manufacture and processing of 1,4-Butynediol as an isolated intermediate under strictly controlled conditions
ES2 (M)	Manufacture and bulk handling of 1,4-Butynediol (flake) in continuous or batch processes
ES3 (F)	Manufacture and bulk handling of 1,4-Butynediol (flake) in continuous or batch processes
ES4 (IS)	Use and handling of coatings, electroplating, cleaning / brightening, and surface application of anti-corrosion solutions containing 1,4-Butynediol
ES5 (IS)	Use of 1,4-Butynediol in laboratories
ES6 (PW)	Use and handling of coatings, electroplating, cleaning / brightening, and surface application of anti-corrosion solutions containing 1,4-Butynediol
ES7 (PW)	Use of 1,4-Butynediol in laboratories

# 2. EXPOSURE SCENARIO 1: MANUFACTURE AND PROCESSING OF 1,4-BUTYNEDIOL AS AN ISOLATED INTERMEDIATE UNDER STRICTLY CONTROLLED CONDITIONS

#### 2.1. DESCRIPTION OF EXPOSURE SCENARIO

Environment contributing scenario(s):	
Manufacture of the substance	ERC 1
Worker contributing scenario(s):	
Chemical production or refinery in closed process without likelihood of exposure or processes with equivalent containment conditions.	PROC 1
Chemical production or refinery in closed continuous process with occasional controlled exposure or processes with equivalent containment conditions	PROC 2
Manufacture or formulation in the chemical industry in closed batch processes with occasional controlled exposure or processes with equivalent containment condition	PROC 3

The activities take place in rigorously contained system with minimisation of release to the environment. The activities take place in rigorously contained system with strict control for manual interventions.

#### 2.2. ENVIRONMENT CONTRIBUTING SCENARIO

#### **2.2.1.** Manufacture of the substance (ERC 1)

#### **2.2.1.1.** Conditions of use

Amount used, frequency and duration of use (or from service life)
<ul> <li>Daily use amount at site: &lt;= 366.7 tonnes/day</li> <li>Annual use amount at site: &lt;= 110000 tonnes/year</li> </ul>
Conditions and measures related to biological sewage treatment plant
<ul> <li>Biological STP: Site specific [Effectiveness Water: 87.34%]</li> <li>Discharge rate of STP: &gt;= 2000 m3/day</li> <li>Application of the STP sludge on agricultural soil: No</li> </ul>
Conditions and measures related to external treatment of waste (including article waste)
• Particular considerations on the waste treatment operations: Closed system required to minimise release to the environment.
Other conditions affecting environmental exposure
• Receiving surface water flow rate: >= 18000 m3/day

#### Fate (release percentage) in the biological sewage treatment plant

The biological STP is site specific and the releases to the various compartments are distributed in the following way:

Release to water	12.66%
Release to air	3.02E-4%
Release to sludge	9.45E-3%
Release degraded	87.33%

#### 2.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	Estimated release factor	Release factor before on site RMM: 0% Release factor after on site RMM: 0% Local release rate: 0 kg/day Explanation: strictly controlled conditions
Air	Estimated release factor	Release factor before on site RMM: 0% Release factor after on site RMM: 0% Local release rate: 0 kg/day Explanation: strictly controlled conditions
Non agricultural soil	ERC based	Release factor after on site RMM: 0.01%

#### 2.3. WORKER CONTRIBUTING SCENARIO

# **2.3.1.** Chemical production or refinery in closed process without likelihood of exposure or processes with equivalent containment conditions (PROC 1)

#### 2.3.1.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form) <i>solid in aqueous solution</i></li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm. Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: One hand face only (240 cm2)</li> </ul>

# **2.3.2.** Chemical production or refinery in closed continuous process with occasional controlled exposure or processes with equivalent containment conditions (PROC 2)

#### 2.3.2.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form) <i>solid in aqueous solution</i></li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm. Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 2.3.3. Manufacture or formulation in the chemical industry in closed batch processes with occasional controlled exposure or processes with equivalent containment condition (PROC 3)

#### 2.3.3.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form) <i>solid in aqueous solution</i></li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other)</li> </ul>

appropriate dermal protection [Effectiveness Dermal: 95%]
<i>EN374</i> gloves, with protection index of at least 2 (breakthrough time >30 min). Nitrile rubber, thickness approx. 0.40 mm.
Chemical protection suit: EN 14605 and EN 13982
Dense rubber boots for cleaning
• Use of eye protection: Yes
Eye and face protection acc. to EN 166
Other conditions affecting workers exposure
Other conditions affecting workers exposure

Place of use: Indoor

• Operating temperature: <= 40.0 °C

• Skin surface potentially exposed: One hand face only (240 cm2)

# 3. EXPOSURE SCENARIO 2: MANUFACTURE - MANUFACTURE AND BULK HANDLING OF 1,4-BUTYNEDIOL (FLAKE) IN CONTINUOUS OR BATCH PROCESSES

#### **3.1. DESCRIPTION OF EXPOSURE SCENARIO**

Environment contributing scenario(s):	
Manufacture of the substance	ERC 1
Worker contributing scenario(s):	
Mixing or blending in batch processes	PROC 5
Transfer of substance or mixture (charging and discharging) at non-dedicated facilities	PROC 8a
Transfer of substance or mixture (charging and discharging) at dedicated facilities	PROC 8b
Transfer of substance or mixture into small containers (dedicated filling line, including weighing)	PROC 9
Tabletting, compression, extrusion, pelletisation, granulation	PROC 14

The activities take place in rigorously contained system with minimisation of release to the environment. The activities take place in rigorously contained system with strict control for manual interventions.

### **3.2. ENVIRONMENT CONTRIBUTING SCENARIO**

#### **3.2.1.** Manufacture of the substance (ERC 1)

#### 3.2.1.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
<ul> <li>Daily use amount at site: &lt;= 35.0 tonnes/day</li> <li>Annual use amount at site: &lt;= 700.0 tonnes/year</li> </ul>
Conditions and measures related to biological sewage treatment plant
<ul> <li>Biological STP: Site specific [Effectiveness Water: 87.34%]</li> <li>Discharge rate of STP: &gt;= 2000 m3/day</li> <li>Application of the STP sludge on agricultural soil: No</li> </ul>
Conditions and measures related to external treatment of waste (including article waste)
• Particular considerations on the waste treatment operations: Closed system required to minimise release to the environment.
Other conditions affecting environmental exposure
• Receiving surface water flow rate: >= 18000 m3/day

#### Fate (release percentage) in the biological sewage treatment plant

The biological STP is site specific and the releases to the various compartments are distributed in the following way:

Release to water	12.66%
Release to air	3.02E-4%
Release to sludge	9.45E-3%
Release degraded	87.33%

#### 3.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	Estimated release factor	Release factor before on site RMM: 0% Release factor after on site RMM: 0% Local release rate: 0 kg/day Explanation: manufacturing of butynediol takes place in a closed system with no releases to the environment
Air	ERC based	Release factor before on site RMM: 5% Release factor after on site RMM: 5% Local release rate: 1.75E3 kg/day
Non agricultural soil	ERC based	Release factor after on site RMM: 0.01%

#### **3.3. WORKER CONTRIBUTING SCENARIO**

#### 3.3.1. Mixing or blending in batch processes (PROC 5)

#### **3.3.1.1.** Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

# **3.3.2.** Transfer of substance or mixture (charging and discharging) at non-dedicated facilities (PROC 8a)

#### 3.3.2.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 3.3.3. Transfer of substance or mixture (charging and discharging) at dedicated facilities (PROC 8b)

### 3.3.3.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training)</li> </ul>

<ul> <li>and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eve and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# **3.3.4.** Transfer of substance or mixture into small containers (dedicated filling line, including weighing) (PROC 9)

#### 3.3.4.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

### 3.3.5. Tabletting, compression, extrusion, pelletisation, granulation (PROC 14)

### **3.3.5.1.** Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

## 4. EXPOSURE SCENARIO 3: FORMULATION OR RE-PACKING -MANUFACTURE AND BULK HANDLING OF 1,4-BUTYNEDIOL (FLAKE) IN CONTINUOUS OR BATCH PROCESSES

#### 4.1. DESCRIPTION OF EXPOSURE SCENARIO

**Product category formulated:** PC 14: Metal surface treatment products, including galvanic and electroplating products; PC 35: Washing and Cleaning Products (including solvent based products); PC 37: Water treatment chemicals; PC 9a: Coatings and Paints, Thinners, paint removers

Environment contributing scenario(s):	
Formulation into mixture	ERC 2
Worker contributing scenario(s):	
Mixing or blending in batch processes	PROC 5
Transfer of substance or mixture (charging and discharging) at non-dedicated facilities	PROC 8a
Transfer of substance or mixture (charging and discharging) at dedicated facilities	PROC 8b
Transfer of substance or mixture into small containers (dedicated filling line, including weighing)	PROC 9
Tabletting, compression, extrusion, pelletisation, granulation	PROC 14

The activities take place in rigorously contained system with strict control for manual interventions.

### 4.2. ENVIRONMENT CONTRIBUTING SCENARIO

#### 4.2.1. Formulation into mixture (ERC 2)

#### 4.2.1.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
<ul> <li>Annual use amount at site: &lt;= 20.0 tonnes/year</li> <li>Daily use amount at site: &lt;= 0.1 tonnes/day</li> <li>Annual amount divided per 200 days of use a year.</li> </ul>
Technical and organisational conditions and measures
<ul> <li>Indoor/outdoor use: Indoor use</li> <li>Process efficiency: Process with efficient use of raw materials.</li> </ul>
Conditions and measures related to biological sewage treatment plant
<ul> <li>Application of the STP sludge on agricultural soil: No</li> <li>Biological STP: Site specific [Effectiveness Water: 87.34%]</li> <li>Discharge rate of STP: &gt;= 2000 m3/day</li> </ul>
Conditions and measures related to external treatment of waste (including article waste)
• Particular considerations on the waste treatment operations: Closed system required to minimise release to the environment.

#### Fate (release percentage) in the biological sewage treatment plant

The biological STP is site specific and the releases to the various compartments are distributed in the following way:

Release to water	12.66%
Release to air	3.02E-4%
Release to sludge	9.45E-3%

#### 4.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 2% Release factor after on site RMM: 2% Local release rate: 2 kg/day
Air	ERC based	Release factor before on site RMM: 2.5% Release factor after on site RMM: 2.5% Local release rate: 2.5 kg/day
Non agricultural soil	ERC based	Release factor after on site RMM: 0.01%

#### 4.3. WORKER CONTRIBUTING SCENARIO

#### 4.3.1. Mixing or blending in batch processes - 100% (PROC 5)

#### 4.3.1.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm. Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

### 4.3.2. Mixing or blending in batch processes - 5% (PROC 5)

#### **4.3.2.1.** Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

### **4.3.3.** Mixing or blending in batch processes - 1% up to 60 °C (PROC 5)

### 4.3.3.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 1.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: Yes (Respirator with APF of 20) [Effectiveness Inhalation: 95%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness</li> </ul>

approx. 0.40 mm. Chemical protection suit: EN 14605 and EN 13982
Dense rubber boots for cleaning • Use of eye protection: Yes Eye and face protection acc. to EN 166
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 60.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 4.3.4. Transfer of substance or mixture (charging and discharging) at non-dedicated facilities – 100% (PROC 8a)

#### 4.3.4.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

# 4.3.5. Transfer of substance or mixture (charging and discharging) at non-dedicated facilities - 5% (PROC 8a)

#### 4.3.5.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 4.3.6. Transfer of substance or mixture (charging and discharging) at dedicated facilities – 100% (PROC 8b)

#### 4.3.6.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training)</li> </ul>

<ul> <li>and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eve and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 4.3.7. Transfer of substance or mixture (charging and discharging) at dedicated facilities - 5% (PROC 8b)

#### 4.3.7.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

# 4.3.8. Transfer of substance or mixture into small containers (dedicated filling line, including weighing) – 100% (PROC 9)

#### 4.3.8.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 4.3.9. Transfer of substance or mixture into small containers (dedicated filling line, including weighing) – 25% (PROC 9)

#### 4.3.9.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training)</li> </ul>

<ul> <li>and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 4.3.10. Transfer of substance or mixture into small containers (dedicated filling line, including weighing) – 5% up to 40 °C (PROC 9)

#### 4.3.10.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

# 4.3.11. Transfer of substance or mixture into small containers (dedicated filling line, including weighing) – 5% up to 60 °C (PROC 9)

#### 4.3.11.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: Yes (Respirator with APF of 20) [Effectiveness Inhalation: 95%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 60.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

#### 4.3.12. Tabletting, compression, extrusion, pelletisation, granulation (PROC 14)

#### 4.3.12.1. Conditions of use

Product (Article) characteristics
<ul> <li>Physical form of the used product: Solid (non or low dusty form)</li> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> </ul>

Gloves: Uvex Rubiflex S or equivalent Chemical protection suit: Microchem 3000 or equivalent • Use of eye protection: Yes Eye and face protection acc. to EN 166 Other conditions affecting workers exposure • Place of use: Indoor • Operating temperature: <= 40.0 °C • Skin surface potentially exposed: Two hands face (480 cm2)

# 5. EXPOSURE SCENARIO 4: USE AT INDUSTRIAL SITES - USE AND HANDLING OF COATINGS, ELECTROPLATING, CLEANING / BRIGHTENING, AND SURFACE APPLICATION OF ANTI-CORROSION SOLUTIONS CONTAINING 1,4-BUTYNEDIOL

#### 5.1. DESCRIPTION OF EXPOSURE SCENARIO

**Product category used:** PC 14: Metal surface treatment products, including galvanic and electroplating products; PC 35: Washing and Cleaning Products (including solvent based products); PC 9a: Coatings and Paints, Thinners, paint removers **Sector of use:** SU 15: Manufacture of fabricated metal products, except machinery and equipment; SU 16: Manufacture of computer, electronic and optical products, electrical equipment

Environment contributing scenario(s):	
Use of non-reactive processing aid at industrial site (no inclusion into or onto article)	ERC 4
Worker contributing scenario(s):	
Industrial spraying	PROC 7
Transfer of substance or mixture (charging and discharging) at non-dedicated facilities	PROC 8a
Transfer of substance or mixture (charging and discharging) at dedicated facilities	PROC 8b
Roller application or brushing	PROC 10
Treatment of articles by dipping and pouring	PROC 13

The activities take place in rigorously contained system with minimisation of release to the environment.

#### 5.2. ENVIRONMENT CONTRIBUTING SCENARIO

# 5.2.1. Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4)

#### 5.2.1.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
<ul> <li>Daily use amount at site: &lt;= 3.0 tonnes/day</li> <li>Annual use amount at site: &lt;= 650.0 tonnes/year</li> </ul>
Technical and organisational conditions and measures
<ul> <li>Process efficiency: Process optimized for highly efficient use of raw materials (II) Typical measures may include e.g.</li> <li>Closed automated process and/or</li> <li>Closed transfer system and/or</li> <li>Centralized process control and/or</li> <li>Centralized process grey water for cleaning</li> <li>optimized and/or automated systems for the transport and handling of raw materials, that minimize overall exposure levels and incidental spills</li> <li>Reduced number of transfer and cleaning operations through e.g.</li> <li>Manufacturing of different products from one premix (masterbatch), to which certain ingredients are added to yield the final products.</li> <li>Dedicated storage tanks for raw materials, premixes and final products Recovery of materials through e.g.</li> <li>Recycling Residues of granular detergents in cleaning steps at packaging or transfer lines into the slurries.</li> </ul>
Conditions and measures related to biological sewage treatment plant
<ul> <li>Biological STP: Site specific [Effectiveness Water: 87.34%]</li> <li>Discharge rate of STP: &gt;= 2000 m3/day</li> <li>Application of the STP sludge on agricultural soil: No</li> </ul>

Conditions and measures related to external treatment of waste (including article waste)

• Particular considerations on the waste treatment operations: Closed system required to minimise release to the environment.

Other conditions affecting environmental exposure

• Receiving surface water flow rate: >= 18000 m3/day

#### Fate (release percentage) in the biological sewage treatment plant

The biological STP is site specific and the releases to the various compartments are distributed in the following way:

Release to water	12.66%
Release to air	3.02E-4%
Release to sludge	9.45E-3%
Release degraded	87.33%

#### 5.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	Estimated release factor	Release factor before on site RMM: 0.07% Release factor after on site RMM: 0.07% Local release rate: 2.1 kg/day Explanation: Closed system: - negligible wastewater emissions as process operates without water contact; - no free product in wastewater stream.
Air	Estimated release factor	Release factor before on site RMM: 40% Release factor after on site RMM: 40% Local release rate: 1.2E3 kg/day Explanation: Negligible air emissions as process operates in a contained system.
Non agricultural soil	ERC based	Release factor after on site RMM: 5%

#### **5.3. WORKER CONTRIBUTING SCENARIO**

#### 5.3.1. Industrial spraying - 5% (PROC 7)

#### 5.3.1.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
• Respiratory Protection: No [Effectiveness Inhalation: 0%]

Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]
EN374 gloves, with protection index of at least 2 (breakthrough time >30 min). Nitrile rubber, thickness approx. 0.40 mm.
Chemical protection suit: EN 14605 and EN 13982
Dense rubber boots for cleaning
Use of eye protection: Yes
Eye and face protection acc. to EN 166
Other conditions affecting workers exposure
Place of use: Indoor
Operating temperature: <= 40.0 °C</li>
Skin surface potentially exposed: Two hands and upper wrists (1500 cm2)

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

### 5.3.2. Industrial spraying - 1% (PROC 7)

#### 5.3.2.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 1.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands and upper wrists (1500 cm2)</li> </ul>

# 5.3.3. Transfer of substance or mixture (charging and discharging) at nondedicated facilities - 25% (PROC 8a)

#### 5.3.3.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 5.3.4. Transfer of substance or mixture (charging and discharging) at non-dedicated facilities- 5% (PROC 8a)

#### 5.3.4.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> </ul>

EN374 gloves, with protection index of at least 2 (breakthrough time >30 min). Nitrile rubber, thickness approx. 0.40 mm. Chemical protection suit: EN 14605 and EN 13982 Dense rubber boots for cleaning • Use of eye protection: Yes Eye and face protection acc. to EN 166 Other conditions affecting workers exposure • Place of use: Indoor • Operating temperature: <= 40.0 °C • Skin surface potentially exposed: Two hands (960 cm2)

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 5.3.5. Transfer of substance or mixture (charging and discharging) at dedicated facilities – 100% (PROC 8b)

#### 5.3.5.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Basic general ventilation (1-3 air changes per hour) [Effectiveness Inhalation: 0%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 20.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

# 5.3.6. Transfer of substance or mixture (charging and discharging) at dedicated facilities - 25% (PROC 8b)

#### 5.3.6.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

# 5.3.7. Transfer of substance or mixture (charging and discharging) at dedicated facilities - 5% (PROC 8b)

#### 5.3.7.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 95%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> </ul>

EN374 gloves, with protection index of at least 2 (breakthrough time >30 min). Nitrile rubber, thickness approx. 0.40 mm.
Chemical protection suit: EN 14605 and EN 13982
Dense rubber boots for cleaning
Use of eye protection: Yes
Eye and face protection acc. to EN 166
Other conditions affecting workers exposure
Place of use: Indoor
Operating temperature: <= 40.0 °C</li>
Skin surface potentially exposed: Two hands (960 cm2)

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

#### 5.3.8. Roller application and brushing - 25% (PROC 10)

#### 5.3.8.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

### 5.3.9. Roller application or brushing - 5% (PROC 10)

### **5.3.9.1.** Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90% Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

### **5.3.10.** Treatment of articles by dipping and pouring - 25% (PROC 13)

#### 5.3.10.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness</li> </ul>

approx. 0.40 mm.
Chemical protection suit: EN 14605 and EN 13982
Dense rubber boots for cleaning
• Use of eye protection: Yes
Eye and face protection acc. to EN 166
Other conditions affecting workers exposure
Place of use: Indoor
• Operating temperature: $\leq 40.0 \text{ °C}$
• Skin surface potentially exposed: Two hands face (480 cm2)

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

### 5.3.11. Treatment of articles by dipping and pouring - 5% (PROC 13)

#### 5.3.11.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: Yes [Effectiveness Inhalation: 90%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

# 6. EXPOSURE SCENARIO 5: USE AT INDUSTRIAL SITES - USE OF 1,4-BUTYNEDIOL IN LABORATORIES

#### 6.1. DESCRIPTION OF EXPOSURE SCENARIO

Product category used: PC 21: Laboratory Chemicals

Environment contributing scenario(s):	
Use of non-reactive processing aid at industrial site (no inclusion into or onto article)	ERC 4
Worker contributing scenario(s):	
Use as laboratory reagent	PROC 15

### 6.2. ENVIRONMENT CONTRIBUTING SCENARIO

# 6.2.1. Use of non-reactive processing aid at industrial site (no inclusion into or onto article) (ERC 4)

#### 6.2.1.1. Conditions of use

Amount used, frequency and duration of use (or from service life)

• Annual use amount at site: <= 1.0 tonnes/year

• Daily use amount at site: <= 0.001 tonnes/day

The default daily use amount is the substance maximum use rate in a typical operation (Msperc). It is the typical maximum site tonnage, based on sector knowledge. 220 emission days/year are assumed.

Technical and organisational conditions and measures

• Indoor/outdoor use: Covers Indoor and Outdoor use

• Type of Process: Solvent based process

• Equipment cleaning: Equipment cleaned with organic solvent, washings are collected and disposed of as solvent waste.

• Process efficiency: Process with efficient use of raw materials.

Conditions and measures related to biological sewage treatment plant

• Application of the STP sludge on agricultural soil: Yes

• Biological STP: Standard [Effectiveness Water: 87.34%]

• Discharge rate of STP: >= 2000 m3/day

Conditions and measures related to external treatment of waste (including article waste)

• Particular considerations on the waste treatment operations

#### 6.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100% Local release rate: 1 kg/day
Air	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100% Local release rate: 1 kg/day
Non agricultural soil	ERC based	Release factor after on site RMM: 5%

### 6.3. WORKER CONTRIBUTING SCENARIO

### 6.3.1. Use as laboratory reagent (PROC 15)

#### 6.3.1.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 8.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Advanced</li> <li>General ventilation: Enhanced general ventilation (5-10 air changes per hour) [Effectiveness Inhalation: 70%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with specific activity training) and (other) appropriate dermal protection [Effectiveness Dermal: 95%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: One hand face only (240 cm2)</li> </ul>

# 7. EXPOSURE SCENARIO 6: WIDESPREAD USE BY PROFESSIONAL WORKERS - USE AND HANDLING OF COATINGS, ELECTROPLATING, CLEANING / BRIGHTENING, AND SURFACE APPLICATION OF ANTI-CORROSION SOLUTIONS CONTAINING 1,4-BUTYNEDIOL

#### 7.1. DESCRIPTION OF EXPOSURE SCENARIO

**Product category used:** PC 14: Metal surface treatment products, including galvanic and electroplating products; PC 35: Washing and Cleaning Products (including solvent based products); PC 9a: Coatings and Paints, Thinners, paint removers **Sector of use:** SU 15: Manufacture of fabricated metal products, except machinery and equipment; SU 16: Manufacture of computer, electronic and optical products, electrical equipment

Environment contributing scenario(s):	
Widespread use of non-reactive processing aid (no inclusion into or onto article, indoor)	ERC 8a
Widespread use of reactive processing aid (no inclusion into or onto article, indoor)	ERC 8b
Widespread use of non-reactive processing aid (no inclusion into or onto article, outdoor)	ERC 8d
Widespread use of reactive processing aid (no inclusion into or onto article, outdoor)	ERC 8e
Worker contributing scenario(s):	
Roller application or brushing	PROC 10
Non industrial spraying	PROC 11
Treatment of articles by dipping and pouring	PROC 13

### 7.2. ENVIRONMENT CONTRIBUTING SCENARIO

# 7.2.1. Widespread use of non-reactive processing aid (no inclusion into or onto article, indoor) (ERC 8a)

#### 7.2.1.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
• Daily local widespread use amount: <= 0.000017 tonnes/day
Conditions and measures related to biological sewage treatment plant
• Biological STP: Standard [Effectiveness Water: 87.34%]
Conditions and measures related to external treatment of waste (including article waste)
Particular considerations on the waste treatment operations

#### 7.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100% Local release rate: 0.017 kg/day
Air	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100%
Non agricultural soil	ERC based	<b>Release factor after on site RMM:</b> 0%

# 7.2.2. Widespread use of reactive processing aid (no inclusion into or onto article, indoor) (ERC 8b)

#### 7.2.2.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
• Daily local widespread use amount: <= 0.000017 tonnes/day
Conditions and measures related to biological sewage treatment plant
• Biological STP: Standard [Effectiveness Water: 87.34%]
Conditions and measures related to external treatment of waste (including article waste)
Particular considerations on the waste treatment operations

#### 7.2.2.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 2% Release factor after on site RMM: 2% Local release rate: 3.3E-4 kg/day
Air	ERC based	Release factor before on site RMM: 0.1% Release factor after on site RMM: 0.1%
Non agricultural soil	ERC based	<b>Release factor after on site RMM:</b> 0%

# 7.2.3. Widespread use of non-reactive processing aid (no inclusion into or onto article, outdoor) (ERC 8d)

#### 7.2.3.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
• Daily local widespread use amount: <= 0.000017 tonnes/day
Conditions and measures related to biological sewage treatment plant
Biological STP: Standard [Effectiveness Water: 87.34%]
Conditions and measures related to external treatment of waste (including article waste)
Particular considerations on the waste treatment operations

#### 7.2.3.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100% Local release rate: 0.017 kg/day
Air	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100%
Non agricultural soil	ERC based	Release factor after on site RMM: 20%

# 7.2.4. Widespread use of reactive processing aid (no inclusion into or onto article, outdoor) (ERC 8e)

### 7.2.4.1. Conditions of use

Amount used, frequency and duration of use (or from service life)
• Daily local widespread use amount: <= 0.000017 tonnes/day
Conditions and measures related to biological sewage treatment plant
• Biological STP: Standard [Effectiveness Water: 87.34%]
Conditions and measures related to external treatment of waste (including article waste)
Particular considerations on the waste treatment operations

#### 7.2.4.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 2% Release factor after on site RMM: 2% Local release rate: 3.3E-4 kg/day
Air	ERC based	Release factor before on site RMM: 0.1% Release factor after on site RMM: 0.1%
Non agricultural soil	ERC based	Release factor after on site RMM: 1%

### 7.3. WORKER CONTRIBUTING SCENARIO

### 7.3.1. Roller application or brushing - 5% (PROC 10)

#### 7.3.1.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training) and (other) appropriate dermal protection [Effectiveness Dermal: 90%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
• Place of use: Indoor

Operating temperature: <= 40.0 °C</li>
Skin surface potentially exposed: Two hands (960 cm2)

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

### 7.3.2. Roller application or brushing - 1% (PROC 10)

#### 7.3.2.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 1.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training) and (other) appropriate dermal protection [Effectiveness Dermal: 90%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands (960 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

#### 7.3.3. Non industrial spraying - 1% (PROC 11)

#### 7.3.3.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 1.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 0.25 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>

Conditions and measures related to personal protection, hygiene and health evaluation
Respiratory Protection: No [Effectiveness Inhalation: 0%]
• Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training)
and (other) appropriate dermal protection [Effectiveness Dermal: 90%]
EN374 gloves, with protection index of at least 2 (breakthrough time >30 min). Nitrile rubber, thickness
approx. 0.40 mm.
Chemical protection suit: EN 14605 and EN 13982
Dense rubber boots for cleaning
• Use of eye protection: Yes
Eye and face protection acc. to EN 166
Other conditions affecting workers exposure
Place of use: Indoor
• Operating temperature: <= 40.0 °C
• Skin surface potentially exposed: Two hands and upper wrists (1500 cm2)

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate chemical protection suit, gloves, goggles/face mask and boots are recommended (described above).

### 7.3.4. Treatment of articles by dipping and pouring - 25% (PROC 13)

#### 7.3.4.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 0.25 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training) and (other) appropriate dermal protection [Effectiveness Dermal: 90%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

### 7.3.5. Treatment of articles by dipping and pouring - 5% (PROC 13)

### **7.3.5.1.** Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 5.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>General ventilation: Basic general ventilation (1-3 air changes per hour) [Effectiveness Inhalation: 0%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training) and (other) appropriate dermal protection [Effectiveness Dermal: 90%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Chemical protection suit: EN 14605 and EN 13982</li> <li>Dense rubber boots for cleaning</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: Two hands face (480 cm2)</li> </ul>

# 8. EXPOSURE SCENARIO 7: WIDESPREAD USE BY PROFESSIONAL WORKERS - USE OF 1,4-BUTYNEDIOL IN LABORATORIES

#### 8.1. DESCRIPTION OF EXPOSURE SCENARIO

Product category used: PC 21: Laboratory Chemicals

Environment contributing scenario(s):

Widespread use of non-reactive processing aid (no inclusion into or onto article, indoor) ERC 8a

#### Worker contributing scenario(s):

Use as laboratory reagent

PROC 15

### 8.2. ENVIRONMENT CONTRIBUTING SCENARIO

# 8.2.1. Widespread use of non-reactive processing aid (no inclusion into or onto article, indoor) (ERC 8a)

#### 8.2.1.1. Conditions of use

• Daily local widespread use amount: <= 0.00000055 tonnes/day
Conditions and measures related to biological sewage treatment plant
Biological STP: Standard [Effectiveness Water: 87.34%]
Conditions and measures related to external treatment of waste (including article waste)
Particular considerations on the waste treatment operations

#### 8.2.1.2. Local releases to the environment

Release	Release estimation method	Explanations
Water	ERC based	Release factor before on site RMM: 100% Release factor after on site RMM: 100% Local release rate: 5.5E-4 kg/day
Air	ERC based	<b>Release factor before on site RMM:</b> 100% <b>Release factor after on site RMM:</b> 100%
Non agricultural soil	ERC based	Release factor after on site RMM: 0%

### 8.3. WORKER CONTRIBUTING SCENARIO

#### 8.3.1. Use as laboratory reagent - 100% (PROC 15)

#### 8.3.1.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 100.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 1.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> </ul>

• Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training) and (other) appropriate dermal protection [Effectiveness Dermal: 90%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: One hand face only (240 cm2)</li> </ul>

PPE is recommended against local demal effects as well as local effects in eyes. Qualitative risk assessment has been done with regards to C&L. Appropriate gloves, goggles/face mask are recommended (described above)

#### 8.3.2. Use as laboratory reagent - 25% formulation (PROC 15)

#### 8.3.2.1. Conditions of use

Product (Article) characteristics
<ul> <li>Percentage (w/w) of substance in mixture/article: &lt;= 25.0 %</li> <li>Physical form of the used product: Solid (non or low dusty form)</li> </ul>
Amount used (or contained in articles), frequency and duration of use/exposure
• Duration of activity: <= 4.0 h/day
Technical and organisational conditions and measures
<ul> <li>Occupational Health and Safety Management System: Basic</li> <li>General ventilation: Good general ventilation (3-5 air changes per hour) [Effectiveness Inhalation: 30%]</li> <li>Local exhaust ventilation: No [Effectiveness Inhalation: 0%, Dermal: 0%]</li> </ul>
Conditions and measures related to personal protection, hygiene and health evaluation
<ul> <li>Respiratory Protection: No [Effectiveness Inhalation: 0%]</li> <li>Dermal protection: Yes (Chemically resistant gloves conforming to EN374 with basic employee training) and (other) appropriate dermal protection [Effectiveness Dermal: 90%]</li> <li>EN374 gloves, with protection index of at least 2 (breakthrough time &gt;30 min). Nitrile rubber, thickness approx. 0.40 mm.</li> <li>Use of eye protection: Yes</li> <li>Eye and face protection acc. to EN 166</li> </ul>
Other conditions affecting workers exposure
<ul> <li>Place of use: Indoor</li> <li>Operating temperature: &lt;= 40.0 °C</li> <li>Skin surface potentially exposed: One hand face only (240 cm2)</li> </ul>